

Revised: 6-15-10
Supersedes: 7-31-08

Ebonite M-250 Product Specification

TEST NAME	TEST METHOD	SPECIFICATIONS		
		Minimum	Maximum	Typical
Viscosity, cSt @ 40° C	D-445			
Viscosity, cSt @ 100° C	D-445	48.7	52.7	50.7
Viscosity, SUS @ 100° F	D-2161			
Viscosity, SUS @ 210° F	D-2161			
Viscosity Index	D-2270			
Gravity, API, 60° F	D-4052	14.7	17.7	16.2
Specific Gravity, 60/60° F	D-1250			.9580
Pounds per Gallon @ 60° F	D-1250			7.978
Flash, COC, °C (°F)	D-92	205 (400)		210 (410)
Pour Point, °C (°F)	D-97		+2 (+36)	-7 (+20)
Color	D-1500			BLACK
Clay-Gel Analysis	D-2007			
Asphaltenes				1.0
Polars				24.8
Aromatics				36.3
Saturates				37.9
Sulfur, % wt.	D-4294			.95
Volatility, 22 hrs @ 225°F	D-972			<0.1